



Registered Data Sheet Perforating System Evaluation, API RP 19B Section 1

API Form 19B-Section 1 Conforms to All Requirements of Section 1 Special Test - See Remarks/Exceptions below

Service Company Available to all from Hunting Explosive weight 12.0 gm, HMX powder, Case Material Zinc
 Gun OD & Trade Name 3-1/8" EXP Gun, 12 SPF 140/20 Degree Max Temp, °F 400 1 hr 3 hr 24 hr 100 hr 200 hr
 Charge Name Charge, 3-1/8" 12G HMX BH Maximum Pressure Rating 20,000 psi, Carrier Material H.T. Steel
 Manufacturer Charge Part No. FLO-3112-411CFZ Date of Manufacture 23 Sep 2009 Shot Density Tested 12 Shots/ft 12
 Gun Type Hollow Steel Carrier, Expendable (HC, E) Recommended Minimum ID for Running 3.58 in.
 Phasing Tested 140/20 degrees, Firing Order: x Top down Bottom up Available Firing Mode: Selective Simultaneous
 Debris Description Acid soluble zinc powder Debris Weight n/a gm/charge, Debris n/a in³/charge

Remarks/Exceptions per Section 1.11 _____

Casing Data 5" OD, Weight 15 lb/ft, API Grade, L-80 Date of Section 1 Test 26 October 2009
 Target Data 30" OD, Amount of Cement 775.5 lb, Amount of Sand 1,551 lb, Amount of Water 406 lb.
 Date of Compressive Strength Test 26 October 2009 Briquette Compressive Strength 5,860 psi, Age of Target 28 days

Shot No.	No 1	No 2	No 3	No 4	No 5	No 6	No 7	No 8	No 9	No 10	No 11
Clearance, in.	0.45	0.78	0.60	0.54	0.82	0.46	0.73	0.67	0.49	0.83	0.49
Casing Hole Diameter, Short Axis, in	0.64	0.48	0.51	0.53	0.44	0.58	0.55	0.48	0.61	0.44	0.53
Casing Hole Diameter, Long Axis, in	0.64	0.58	0.57	0.61	0.50	0.59	0.57	0.55	0.65	0.50	0.63
Average Casing Hole Diameter, in.	0.64	0.53	0.54	0.57	0.47	0.59	0.56	0.52	0.63	0.47	0.58
Total Depth, in.	4.80	4.55	4.55	4.43	4.30	4.30	4.43	4.80	5.05	4.55	4.80
Burr Height, in.	0.03	0.05	0.05	0.04	0.06	0.03	0.04	0.05	0.07	0.05	0.11

Shot No.	No 12	No 13	No 14	No 15	No 16	No 17	No 18	No 19	No 20	No 21	No 22	Average
Clearance, in.	0.67	0.73	0.46	0.82	0.54	0.60	0.78					XXXXXX
Casing Hole Diameter, Short Axis, in	0.55	0.47	0.55	0.46	0.50	0.56	0.44					0.52
Casing Hole Diameter, Long Axis, in	0.59	0.53	0.58	0.53	0.58	0.62	0.58					0.58
Average Casing Hole Diameter, in.	0.57	0.50	0.57	0.50	0.54	0.59	0.51					0.55
Total Depth, in.	4.30	4.68	4.55	4.80	5.55	4.80	5.05					4.68
Burr Height, in.	0.11	0.07	0.06	0.04	0.04	0.10	0.06					0.06

Remarks _____

Manufacturer's Certification

Type of Certification: _____ Self Third Party _____ API Witnesses: Jim Stout & Mona Elkhatib

I certify that these tests were made according to the procedures as outlined in API 19B: Recommended Practice for Evaluation of Well Perforators, Second Edition, September 2006. All of the equipment used in these tests, such as the guns, jet charges detonator cord, etc., was standard equipment with our company for the use in the gun being tested and was not changed in any manner for the test. Furthermore, the equipment was chosen at random from stock and therefore will be substantially the same as the equipment that would be furnished to perforate a well for any operator. API neither endorses these tests nor recommends the use of the perforator system described.

CERTIFIED BY T. J. Stout President, Hunting Titan 4/8/2014 143 HCR 4361, Milford, TX 76670, USA
 RECERTIFIED _____ (Company Official) _____ (Title) _____ (Date) _____ (Company) _____ (Address)

Name of test as it should appear on website: 3.13-in. EXP 12 SPF w/ BH FLO-3112-411CFZ

Name of test as it appears on application and application date: FLO-3112-411CFZ, Charge, 3-1/8" 12G HMX BH (Appl: 13 Aug 2009, revised 19 Oct 2009)